

# PORFYRIOS

## CHAP GLASS



GLAZING NAME	<b>PG_ ENERGY N</b>		
GLAZING DESIGN	PANE 1	SPACER	PANE 2
	6mm ENERGY_N pos 2	16 mm - Air	6mm Clear

### THERMAL PROPERTIES (EN 673)

Ug-Value (W/m <sup>2</sup> )	<b>1.3</b>
------------------------------	------------

### LIGHT PROPERTIES (EN 410)

Light Transmission - $\tau_v$	<b>72</b>
Light Reflection - $\rho_v$	<b>12</b>
Internal light reflection -	<b>13</b>
Color Rendering - RD65 - R	<b>95</b>

### ENERGY PROPERTIES (EN 410)

Solar factor - g (%)	<b>40</b>
Energy Reflection - $\rho_e$	<b>31</b>
Shading coefficient – SC	<b>0.46</b>
Total Energy absorption -	<b>33</b>

### OTHER PROPERTIES

Direct airborne sound insulation (Rw (C;Ctr) - EN 12758) – dB (EN 12758)	<b>32(-1 -3)</b>
Burglar Resistance - EN 356	<b>NPD</b>
Pendulum body impact resistance - EN 12600	<b>NPD</b>
Resistance to fire - EN 13501-2	<b>NPD</b>

### MANUFACTURING PROPERTIES (EN 410)

Nominal thickness – (mm)	<b>28</b>
Weight - (Kg/m <sup>2</sup> )	<b>30</b>

### Remarks

The data are calculated using spectral measurements that are conform to standards EN 410, ISO 9050 (1990) and WIS/WINDAT. The Ug-value (formerly k-value) is calculated according to standard EN 673. The emissivity measurement complies with standards EN 673 (Annex A) and EN 12898. This document is no evaluation of the risk of glass breakage due to thermal stress. For tempered glass: the risk of spontaneous breakage due to Nickel-Sulfide is not covered by PorfyriosGlass. The Heat Soak Test is available on request. Specifications, technical and other data are based on information available at the time of preparation of this document and are subject to change without notice. Porfyrios Glass cannot be held responsible for any deviation between the data introduced and the conditions on site. These sound reduction indexes correspond to glazings which are 1,23 by 1,48m according to EN ISO 10140-3 and are tested in laboratory conditions. In-situ performances may vary according to the effective glazing dimensions, frame system, noise sources etc. The accuracy of the given indexes is not better than +/- 1dB.

19 Spyrou Kyprianou, Ergates Industrial Area, P.O. BOX 28343 - 2093 Nicosia - CyprusTel, +357 22487910, 22571016, Fax +357 487910, email: [porfyriosglass.com.cy](mailto:porfyriosglass.com.cy),