



GLAZING NAME	PG_PLANISTAR SUN		
	PANE 1	SPACER	PANE 2
GLAZING DESIGN	6mm PLANISTAR SUN pos 2 thermally toughened Heat Soak 8hr	16 mm - Argo 90%	44.1 mm Laminated Clear 1,52 PVB Thermally Toughened Heat Soaked 8hr

THERMAL PROPERTIES (EN 673)

Ug-Value (W/m ²)	1.0
------------------------------	------------

LIGHT PROPERTIES (EN 410)

Light Transmission - ν	69
Light Reflection - ν	13
Internal light reflection -	14
Color Rendering - RD65 - R	92

ENERGY PROPERTIES (EN 410)

Solar factor - g (%)	37
Energy Reflection - e	32
Shading coefficient – SC	0.43
Total Energy absorption -	32

OTHER PROPERTIES

Direct airborne sound insulation (Rw (C;Ctr) - EN 12758) – dB (EN 12758)	NPD
Burglar Resistance - EN 356	NPD
Pendulum body impact resistance - EN 12600	1C2-2B2
Resistance to fire - EN 13501-2	NPD

MANUFACTURING PROPERTIES (EN 410)

Nominal thickness – (mm)	31.5
Weight - (Kg/m ²)	36.6

Remarks

The data are calculated using spectral measurements that are conform to standards EN 410, ISO 9050 (1990) and WIS/WINDAT. The Ug-value (formerly k-value) is calculated according to standard EN 673. The emissivity measurement complies with standards EN 673 (Annex A) and EN 12898. This document is no evaluation of the risk of glass breakage due to thermal stress. For tempered glass: the risk of spontaneous breakage due to Nickel-Sulfide is not covered by PorfyriosGlass. The Heat Soak Test is available on request. Specifications, technical and other data are based on information available at the time of preparation of this document and are subject to change without notice. Porfyrios Glass cannot be held responsible for any deviation between the data introduced and the conditions on site. These sound reduction indexes correspond to glazings which are 1,23 by 1,48m according to EN ISO 10140-3 and are tested in laboratory conditions. In-situ performances may vary according to the effective glazing dimensions, frame system, noise sources etc. The accuracy of the given indexes is not better than +/- 1dB.

19 Spyrou Kyprianou, Ergates Industrial Area, P.O. BOX 28343 - 2093 Nicosia - CyprusTel, +357 22487910, 22571016, Fax +357 487910, email: porfyriosglass.com.cy,